NOTES:

- SUBSTRATE
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec
- COATING (APPLY ACROSS COATING APERTURE) PERFORMANCE SPECIFICATIONS:

T(avg): >85% FROM 400 - 580nm FOR RANDOM POLARIZATION @ 45° AOI T(abs): >80% FROM 400 - 580nm FOR ALL POLARIZATIONS @ 45° AOI R(avg): >97% FROM 625 - 795nm FOR RANDOM POLARIZATION @ 45° AOI R(abs): >95% FROM 625 - 795nm FOR ALL POLARIZATIONS @ 45° AOI

S1

PLANO 40-20

24.2 x 34.6

24.2 x 34.6

PROTECTIVE AS NEEDED | PROTECTIVE AS NEEDED


T(abs): = 50% 600nm @ 45° AOI

GDD: 80 ± 30fs² @ 410 - 580nm 120 ± 80fs² @ 400 - 580nm

\$1: HARD COATED \$2: SINGLE LAYER MgF2

4. FINE GRIND SURFACE

- POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION RMS@ 632.8nm ≤ ¼ λ
- 7. ROHS COMPLIANT



SHORTPASS FILTER

SHAPE

BEVEL


SURFACE QUALITY


CLEAR APERTURE

COATING APERTURE

	Ī
S2	
PLANO	
40-20	
24.2 x 34.6	THIRD AI PROJEC
24.2 x 34.6	







SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

Edmund Optic	S®
---------------------	----

RD ANGLE . OJECTION	\$	TITLE	600nm, 25.2 x 35.6mm, Low GDD Dichroic Shortpass Ultrafast Filter	
l DIMS IN	mm	DWG NO	14011	SHEET 1 OF 1